

Duncan® Mid-Range Performance Index

Although the majority of Duncan® fired products are designed for low-fire applications, many perform well at mid-range temperatures. Listed below are the characteristics of each Duncan® product when fired to cone 6.

Envision® Glazes

- IN 1001 Clear Not recommended for cone 6 firing.
- IN 1002 Nordic Light Glossy with yellow tones. Crazing will occur.
- IN 1003 Sun Yellow Not recommended for cone 6 firing.
- IN 1004 Sunset Red Not recommended for cone 6 firing.
- IN 1005 Ruby Red Not recommended for cone 6 firing.
- IN 1006 Tearose Smooth glossy surface. Rose color fades to pale brown. Crazing may occur.
- IN 1007 Carnation Pink Not recommended for cone 6 firing.
- IN 1009 Cherry Red Color will creep, bubble and fade significantly. May craze.
- IN 1010 Plum Blush Smooth and glossy. Red burns away completely. Color fades to light purple.
- IN 1011 Royal Purple Not recommended for cone 6 firing.
- IN 1012 Orchid Not recommended for cone 6 firing.
- IN 1013 Denim Blue Not recommended for cone 6 firing.
- IN 1014 Galaxy Blue Color holds well to deep cobalt blue. Glossy surface. Slight crazing tendency.
- IN 1015 Caribbean Blue Smooth and glossy. Color fades to pale transparent green. Crazing may occur.
- IN 1016 Peacock Smooth and glossy. Nice deep green. Crazing may occur.
- IN 1017 Sea Mist Green Smooth and glossy. Color becomes greener. Heavy crazing.
- IN 1018 Celadon The glaze will creep and color will burn out. Crazing may occur.
- IN 1019 Holiday Green Smooth and glossy. Mottled effect in detail areas. Crazing will occur.
- IN 1021 Terra-Cotta Not recommended for Cone 6 firing.
- IN 1022 Peach Blush Color burns away. Glossy surface with a slight texture. Crazing may occur.
- IN 1023 Butter Toffee Fades to a pale caramel color.
- IN 1026 Very Black Not recommended for Cone 6 firing.
- IN 1027 Spiced Cream Not recommended for Cone 6 firing.
- IN 1028 Grey Spice Color fades and the specks bleed. Crazing may occur.
- IN 1029 Tweed Not recommended for Cone 6 firing.
- IN 1030 Cornmeal Pale yellow, mostly opaque. Crazing will occur.
- IN 1031 Antique Peach Nice blue-peach. Nice surface, but less glossy.
- IN 1032 Miami Pink Pink turns to grey-white. Glossy, crinkled surface.
- IN 1033 Bluebonnet Glossy blue. Mostly transparent with an alligator finish where glaze is applied thickly.
- IN 1034 Larkspur Glossy. Deep to medium cobalt blue.
- IN 1035 Rain Tree Green Very glossy. Minimal color change. A little less opaque.
- IN 1037 Leaf Green Turns to glossy green-brown. Crazing may occur.
- IN 1038 Parchment Clear to light beige with a glossy surface.
 Crazing will occur.
- IN 1039 Mocha Cream Glossy. Yellowish toffee color. Crazing may occur.
- IN 1042 Grey Color is a nice glossy yellow-grey with darker highlights in detail areas.

- IN 1043 Driftwood Nice gloss. Color is a lighter yellowish mint green.
- IN 1044 Sand Diego Color is a nice glossy reddish flesh tone.
- IN 1045 Romaine Glossy. Color is a nice blue-grey tone.
- IN 1047 Roasted Pepper Color loses red value. Nice medium yellow-brown gloss. May craze.
- IN 1048 Delphinium Deeper blue. Nice light breakup pattern.
- IN 1049 Sand Bar Glossy, darker speckled tan.
- IN 1050 Oregano Dark, deeper brown speckle with red highlights on detail.
- IN 1051 Paprika Cream Glossy. Medium speckled brown.
- IN 1053 Harvest Color remains true. Semi-gloss, semi-opaque surface.
- IN 1055 Grape Color shifts to a medium reddish blue. Gloss, semitransparent surface. Crazing will occur.
- IN 1056 Aqua Fresca Color is a yellower tone with some mottling. Glossy, semi-opaque surface.
- IN 1057 Iced Mint Color shifts to a greenish grey with some mottling where thick. Glossy, opaque surface.
- IN 1058 Clover Slightly more olive shade with some small mottling. Glossy, semiopaque surface.
- IN 1059 Light Pink Color fades. Very transparent.
- IN 1060 Bright Wine Color fades. Very transparent.
- IN 1061 Light Kelp Color darkens to forest green. Very transparent and fluid.
- IN 1062 Light Kiwi Color darkens. Very transparent.
- IN 1064 Baby Blue Transparent color; fluid.
- IN 1065 Light Turquoise Color fades. Very transparent and fluid. Crazing will occur.
- IN 1066 Blueberry Spice Color fades. Very transparent and fluid. Crazing will occur.
- IN 1067 Grape Spice Color fades and changes from pink/purple to cream color.
- IN 1068 Ocean Mist Color slightly darker shade. Specks are slightly more fluid.
- IN 1071 Lemon Color darkens. Slightly fluid.
- IN 1072 Baroque Gold Color darkens.
- IN 1073 Strawberry Color darkens. Crazing will occur. Fluid.
- IN 1074 Cranberry Not recommended for cone 6 firing.
- IN 1075 Cobalt Blue Color darkens. Semitransparent. Very fluid.
- IN 1076 Federal Blue Color darkens to navy blue. Semi-transparent.
- IN 1078 Key Lime Not recommended for cone 6 firing.
- IN 1079 Turquoise Not recommended for cone 6 firing.
- IN 1081 Cocoa Color shift to lighter shade of brown. Slightly fluid.
- IN 1082 Chocolate Brown Color shift to lighter shade of brown.
- IN 1100 White Not recommended for cone 6 firing.
- IN 1105 Federal Blue Color darkens. Fluid.
- IN 1116 Emerald Bay Not recommended for cone 6 firing.
- IN 1201 Neon Yellow Dull color.
- IN 1202 Neon Blue Dull, darker color. Semitransparent.
- IN 1203 Neon Chartreuse Color shift to light lime green.
 Transparent. Crazing will occur.
- IN 1204 Neon Orange Color darkens.



Envision® Glazes (continued)

- IN 1205 Neon Green Color darkens to a shade of dark olive. Transparent. Fluid.
- IN 1206 Neon Red Not recommended for cone 6 firing.
- IN 1603 Autumn Very fluid. No green shades, color shift to dark chocolate brown.
- IN 1613 Black No color change.
- IN 1626 Royal Ruby Not recommended for cone 6 firing.
- IN 1627 Clear Black Glossy, medium blue-grey. Some crazing may occur.
- IN 1629 Ivory Belleek Not recommended for Cone 6 firing.
- IN 1634 Royal Blue Glossy, deep dark blue. Very fluid.
- IN 1639 Apple Green Color shift to seafoam green. Crazing will occur. Very fluid.

- IN 1640 Foliage Green Light olive green gloss. Some crazing may occur. Very fluid.
- IN 1653 Downright White Satiny white.
- IN 1666 Walnut Brown Warm medium caramel gloss.
- IN 1667 Caramel Very fluid. Some crazing may occur.
- IN 1669 Bottle Green Very fluid. Crazing will occur. Color shift to dark yellow-green.
- IN1670 Sun Yellow Dull color. Crazing will occur.
- IN 1673 Espresso Light tan semitransparent gloss.
- IN 1679 Royal Danish Transparent color, fluid.
- IN 1781 Pumpkin Orange Pale greenish-yellow gloss.

Crystals™ Glazes and Crackles™ Glazes

- CR 800 Clear Glossy clear.
- CR 821 Parchment Crackle Glossy greenish brown.
- CR 822 Mocha Cream Crackle Glossy. Color shift to yellow.
- CR 823 Celadon Crackle Glossy, yellow celadon.
- CR 850 Cumulus Clouds Very fluid. Crystals become transparent in color.
- CR 851 Eternal Galaxy Crystals become very fluid.
- CR 852 Solar Flares Crystals become very fluid. Base color becomes darker. Semi-gloss.
- CR 853 Sailor's Delight Not recommended for cone 6 firing.
- CR 854 Outer Space Very fluid. Crazing will occur.
- CR 855 Water Lily Marsh Very fluid. Crystals become dark brown and base color becomes darker.
- CR 856 Ancient Woodland Crystals become fluid. Glaze turns to a darker, semi-gloss shade.
- CR 857 Alpine Meadow Very fluid. Crazing will occur.
- CR 858 Polynesian Lagoon Very fluid, crazing will occur. Base color changed from lavender to clear/yellow.
- CR 859 African Savanna Very fluid, crazing will occur.
- CR 901 Waterfall Blackish blue with spots and runs. Crystals disappear. Very fluid. Crazing will occur.
- CR 902 Night Sky Deep cobalt blue with light areas. Glossy surface.
 Very fluid. Crazing will occur.
- CR 903 Emerald Falls Glossy olive green with light areas. Very fluid.
 Crazing will occur.
- CR 904 Fudge Marble Glossy yellowish brown with light streaks, black spots and runs. Very fluid. Crazing will occur.
- CR 905 Blueberries Glossy with streaks of blue and green. Very fluid.
 Crazing will occur.

- CR 906 Peppered Raspberry Glossy. Fades to blueish lavender with streaks of black and green. Very fluid. Crazing will occur.
- CR 907 La Fiesta Glossy red-blue with faint white spots and green streaks. Very fluid. Crazing will occur.
- CR 908 Monet's Garden Glossy blue with streaks of green and yellow. Very fluid. Crazing will occur.
- CR 909 Moss Green Glossy forest green with patterns of white and olive green. Very fluid. Crazing will occur.
- CR 910 Forest Moss Glossy green-brown with spots of olive green and teal. Very fluid. Crazing will occur.
- CR 911 Ocean Mist Glossy blue-olive green with black streaks. Very fluid. Crazing will occur.
- CR 912 Spring Meadow Glossy yellow-green with black spots and streaks. Very fluid. Crazing will occur.
- CR 913 Cranberry Frost Glossy. Milky clear with a pink tint and streaks of black. Very fluid. Crazing will occur.
- CR 914 Grape Splash Medium reddish blue with specks of lavender. Glossy semitransparent surface. Crazing may occur.
- CR 915 Night Frost Deep cobalt blue with specks of crystal color.
 Glossy semi-opaque surface. Crazing may occur.
- CR 916 Holly Berries Crystals become very fluid and transparent.
- CR 917 Caramel Latte Crystals become very fluid.
- CR 918 Cherry Blossoms Crystals become clear. Base color is a lighter, semi-gloss.
- CR 919 Milky Way Semi-gloss. Crystals become white.
- CR 920 Water Lilies Crystals become very fluid.
- CR 921 Glacier Storm Crystals become a duller shade of blue.
- CR 20095 Blue Enamelware Royal blue gloss background with light frosting of white.

French Dimensions™

- FD 254 Black Licorice Color flattens at mid-range.
- FD 258 Pure White Color flattens at mid-range.
- FD 265 French Straw Color flattens at mid-range.
- FD 266 French Papaya Color flattens at mid-range.
- FD 267 French Scarlet Color flattens at mid-range.
- FD 268 French Wine Color flattens at mid-range.
- FD 269 French Plum Color flattens at mid-range.
 FD 270 French Delft Color flattens at mid-range.
- FD 271 French Kiwi Color flattens at mid-range.

- FD 272 French Briarwood Color flattens at mid-range.
- FD 274 Light Pink Color flattens at mid-range. Color becomes clear. Crazing may occur.
- FD 275 Neon Blue Color flattens at mid-range.
- FD 276 Neon Chartreuse Color flattens at mid-range.
- FD 277 Neon Coral Color flattens at mid-range.
- FD 278 French Really Red Color flattens at mid-range.
- FD 279 French Navy Color flattens at mid-range.
 FD 280 French Hunter Color flattens at mid-range.

Concepts® Underglazes For Bisque & Majolica

- CN 011 Light Straw Slight shift in color to the green side. Nice glossy opaque surface.
- CN 012 Bright Straw Not recommended for cone 6 firing.
- CN 013 Dark Straw Not recommended for cone 6 firing.
- CN 021 Light Saffron Color true. Glossy opaque surface.
- CN 022 Bright Saffron Color true. Glossy semi-opaque surface.
- CN 031 Light Butternut Color true. Glossy opaque surface.
- CN 032 Bright Butternut Color true. Glossy semi-opaque surface.
- CN 033 Dark Butternut Not recommended for cone 6 firing.
- CN 041 Light Papaya Color true. Glossy opaque surface.
- CN 042 Bright Papaya Color true. Glossy semi-opaque surface.
- CN 043 Dark Papaya Color true. Glossy semi-opaque surface.
- CN 052 Bright Tangerine Slightly darker color shade. Glossy semiopaque surface.
- CN 061 Light Salsa Color true. Glossy semi-opaque surface.
- CN 062 Bright Salsa Color true. Glossy semi-opaque surface.
- CN 063 Dark Salsa Not recommended for Cone 6 firing.
- CN 071 Light Scarlet Slightly bluer color shade. Glossy opaque surface.
- CN 072 Bright Scarlet Slightly darker color shade. Glossy semiopaque surface.
- CN 073 Dark Scarlet Slightly darker color shade. Glossy semiopaque surface.
- CN 074 Really Red Not recommended for cone 6 firing.
- CN 081 Light Wine Color is much stronger. Glossy semitransparent surface
- CN 082 Bright Wine Color is a deeper wine. Glossy semitransparent surface.
- CN 083 Dark Wine Not recommended for cone 6 firing.
- CN 101 Light Heather Color true but some mottling where thick. Glossy opaque surface.
- CN 102 Bright Heather Color is a lighter shade and some mottling where thick. Glossy opaque surface.
- CN 103 Dark Heather Color is a lighter shade and some mottling where thick. Glossy opaque surface.
- CN 111 Light Delft Color true but some mottling where thick. Glossy opaque surface.
- CN 112 Bright Delft Color is deeper with slight mottling where thick. Glossy opaque surface.
- CN 113 Dark Delft Color is a nice deep cobalt blue. Glossy semiopaque surface.
- CN 121 Light Nautical Color is a little darker. Glossy opaque surface.
- CN 122 Bright Nautical Color is deeper with slight mottling where thick. Glossy opaque surface.
- CN 123 Dark Nautical Color is deeper and yellower with some mottling where thick. Glossy opaque surface.
- CN 131 Light Tidepool Color is yellower with some mottling where thick. Glossy semi-opaque surface.
- CN 132 Bright Tidepool Color is a medium greenish blue. Glossy opaque surface.
- CN 133 Dark Tidepool Color is a deep greenish blue. Glossy opaque
- CN 141 Light Aqua Color true. Glossy semi-opaque surface.
- CN 142 Bright Aqua Color is a yellower blue. Glossy semitransparent surface
- CN 151 Light Blue Spruce Color true. Glossy semi-opaque surface.
- CN 152 Bright Blue Spruce Color is a yellower tone. Glossy semiopaque surface.
- CN 153 Dark Blue Spruce Color is lighter and brighter with dark areas where thick. Glossy opaque surface.
- CN 161 Light Wintergreen Color shifts to a greenish gray with some mottling where thick. Glossy opaque surface.
- CN 162 Bright Wintergreen Color shifts to a deep forest green.
 Glossy semi-opaque surface.

- CN 163 Dark Wintergreen Color darkens. A little fluid.
- CN 171 Light Kelp Color shifts to a dark leaf green color. Glossy semi-opaque surface.
- CN 172 Bright Kelp Color shifts to a darker shade. Glossy opaque surface.
- CN 173 Dark Kelp Slightly bluer shade of green with olive green thick areas. Glossy opaque surface.
- CN 181 Light Kiwi Slightly more olive shade with some mottling.
 Glossy semi-opaque surface.
- CN 182 Bright Kiwi Color is a darker more olive tone. Glossy opaque surface.
- CN 183 Dark Kiwi Color is a deep black-olive green. Glossy opaque surface.
- CN 201 Light Grey Color shift from grey to seafoam green.
- CN 202 Bright Grey Color is a paler, more yellow grey. Glossy opaque surface.
- CN 203 Dark Grey Color is a strong blue-grey with mottling in heavy areas. Glossy opaque surface.
- CN 211 Light Taupe Color shifts to a yellow-green tint. Glossy semiopaque surface.
- CN 212 Bright Taupe Slightly bluer tone. Glossy semi-opaque surface.
- CN 213 Dark Taupe Reddish-brown color. Semi-gloss surface with a slight texture.
- CN 221 Light Blush Color is a slightly bluer flesh tone. Glossy opaque surface.
- CN 222 Bright Blush Color is a bluer pink tone. Glossy opaque surface.
- CN 232 Bright Briarwood Color is a lighter yellow-brown. Glossy opaque surface.
- CN 233 Dark Briarwood Color is a deep yellow-brown. Glossy opaque surface.
- CN 241 White Color true. Glossy semi-opaque surface.
- CN 244 Really White Semitransparent.
- CN 253 Black Color true. Glossy semi-opaque surface.
- CN 261 Light Grape Color shift to a lighter shade of purple.
- CN 262 Bright Grape Color shift from purple to blue/purple.
- CN 263 Dark Grape Color shift from dark purple to dark blue. Fluid.
- CN 271 Light Jade Color darkens.
- CN 272 Bright Jade Color darkens. A little fluid.
- CN 281 Light Brown Color shift from light brown to seafoam green. Slightly fluid. Transparent.
- CN 282 Bright Brown Color shift from brown to a light caramel shade. Fluid. Leaves scale-like effect.
- CN 291 Light Purple Color fades. Transparent.
- CN 292 Bright Purple Color shift from purple to blue/grey.
- CN 293 Dark Purple Color shift from dark purple to dark blue. Fluid.
- CN 302 Bright Caribbean Color darkens and is more blue than green. A little fluid.
- CN 311 Light Ginger Color darkens.
- CN 312 Bright Ginger Color shifts to more of a brown and less orange.
- CN 313 Dark Ginger Color darkens.
- CN 322 Bright Plum Color darkens.
- CN 331 Light Olive Color shift to a grey/green. A little fluid.
- · CN 332 Bright Olive Color darkens.
- CN 333 Dark Olive Not recommended for cone 6 firing.
- CN 341 Light Pink Color darkens slightly.
- CN 342 Bright Pink Color darkens slightly.
- CN 343 Dark Pink Color darkens.
- CN 501 Neon Yellow Dull color. Semitransparent.
- · CN 502 Neon Blue Color darkens slightly.
- CN 503 Neon Chartreuse Color shift slightly to the green side.
- CN 504 Neon Orange Color darkens.

Concepts® Underglazes For Bisque & Majolica (continued)

- CN 505 Neon Green Color darkens significantly.
- CN 506 Neon Coral Color darkens.
- CN 507 Neon Red Not recommended for cone 6 firing.
- CN 508 Chutney Spice Color darkens slightly.
- CN 509 Paprika Red Color darkens.

- CN 510 Earthen Moss Color shift to the green side.
- CN 511 Sunflower Yellow Color darkens.
- CN 512 Green Apple Color darkens.
- CN 513 Deep Berry Color fades to a light purple with specks of darker purple.

Cover-Coat® Opaque Underglazes

- CC 101 Arctic White Off-white satin.
- CC 102 Ivory Pearl Medium beige satin.
- CC 103 Lotus Yellow Medium beige satin.
- CC 105 Sungold Yellow Rich gold gloss.
- CC 106 Harvest Gold Greyed apricot gloss.
- CC 108 Miami Pink Deep pink matte finish.
- CC 109 Sunset Pink Soft light pink satin.
- CC 111 Dresden Flesh Slightly beige gloss.
- CC 112 Light Flesh Light brown gloss.
- CC 117 Walnut Brown Dark brown satin.
- CC 118 Cobalt Crystal Black Jet black satin.
- CC 119 Charcoal Deep blue-green gloss.
- CC 120 Samoa Taupe Soft grey satin.
- CC 121 Temple Grey Blue-grey gloss.
- CC 122 Moonstone Grey Pale grey-green satin.
- CC 126 Spring Green Medium green with a dull surface.
- CC 127 Fern Green Medium brown with slight green tinge. Matte surface.
- CC 128 Everglade Green Rich olive green matte.
- CC 129 Forest Green Warm earthy brown matte.
- CC 131 Teal Blue Deep blue-green gloss.
- CC 132 Fiesta Turquoise Deep turquoise satin.
- CC 133 Turquoise Medium turquoise satin.
- CC 134 Stardust Blue Medium grey-blue gloss.
- CC 135 Lake Blue Medium blue gloss.
- CC 136 Marlin Blue Deep royal blue gloss.
 CC 137 Regency Purple Pale lilac gloss.
- CC 140 Morocco Red Color fades almost completely. Matte surface.
- CC 141 Light Yellow Slightly greyed light yellow. Satin.
- CC 142 Canary Yellow Slightly greyed bright yellow. Satin.
- CC 143 Yellow Orange Greyed gold satin.
- CC 144 Burnt Orange Medium brown gloss.
- CC 145 Indian Red Greyed rusty brown matte.
- CC 146 Purple Medium orchid gloss.
- CC 148 Deep Turquoise Deep greyed turquoise satin.
- CC 150 Medium Green Greyed medium green satin.
- CC 151 Rose Very pale orchid gloss.
- CC 152 Peach Rosy pink matte.

- CC 153 Avocado Greyed olive green gloss.
- CC 154 Cobalt Navy Blue Deep navy blue gloss.
- CC 156 Medium Brown Medium, warm reddish-brown satin.
- CC 157 Darkest Brown Very dark brown gloss.
- CC 158 Bright Green Intense bright green matte.
- CC 159 Bright Blue Lively bright blue satin.
- CC 160 Deep Purple Blue-grey gloss.
- CC 161 Blue Green Greyed blue-green matte.
- CC 163 Danish Blue Dark rich blue gloss.
- CC 164 Ice Grey Medium grey matte.
- CC 165 Black Brown Black matte.
- CC 169 Peaches 'n Cream Mustard yellow satin.
- CC 171 Butterscotch Medium brown gloss.
- CC 172 Plum Blossom Medium blue gloss.
- CC 173 Cobblestone Light olive mottled gloss.
- CC 174 Kentucky Bluegrass Deep jade gloss.
- CC 178 Pecos Pink Medium pink matte.
- CC 180 Papago Turquoise Turquoise matte.
- CC 181 Indian Summer Dark brown satin.
- CC 182 Watermelon Red Dark pink gloss. Slightly fluid.
- CC 183 Cherry Red Dark rose gloss. Slightly fluid.
- CC 184 Orange Peel Dark orange gloss. Slightly fluid.
- CC 185 Apricot Slightly darker orange. Slightly fluid.
- CC 186 Tomato Red Slightly darker rose. Matte finish. Slightly fluid.
- CC 187 Rustic Red Slightly darker pink. Matte finish. Slightly fluid.
- $\bullet \ \mathsf{CC} \ \mathsf{188} \ \mathsf{Lilac} \mathsf{Transparent} \ \mathsf{blue} \ \mathsf{gloss}. \ \mathsf{Slightly} \ \mathsf{fluid}.$
- CC 190 Baby Blue Transparent light blue. Slightly fluid.
- CC 191 Marine Blue Darker, transparent blue. Slightly fluid.
- CC 192 Dark Blue Darker blue gloss.
- CC 193 Hunter Green Darker forest green gloss.
- CC 194 Red Wagon Darker red matte.
- CC 201 Neon Yellow Neon yellow semi-gloss.
- CC 202 Neon Blue Teal semi-gloss.
- CC 203 Neon Chartreuse Darker lime green semi-gloss.
- CC 204 Neon Orange Darker orange.
- CC 205 Neon Green Darker hunter green. Transparent. Semi-gloss.
- CC 206 Neon Red Dark red, semi-gloss.

<u>E-Z Stroke™ Translucent Underglazes</u>

- EZ 002 Cinderella Pink Slight sheen. Much more intense pink.
- EZ 003 Irish Green Dull, yellower lime green.
- EZ 004 Willow Yellow Dull, color remains true.
- EZ 005 Sierra Yellow Color fades.
- EZ 006 Forget-Me-Not Blue Nice satin sheen. Medium blue.
- EZ 007 Royal Purple Color fades.
- EZ 008 Ruby Red Color fades.
- EZ 010 French Brown Slight gloss. Much deeper chocolate brown.
- EZ 011 Sienna Brown Slightly glossy. Much stronger, light brown.
- EZ 012 Cobalt Jet Black Dull black.
- EZ 013 White Not recommended for cone 6 firing.
- EZ 014 Jade Green Glossy blue-green.
- EZ 016 Grass Green Color dulls. Much bluer green.

- EZ 017 Dark Turquoise Color dulls. Very little color change.
- EZ 018 Chartreuse Dull lime green.
- EZ 019 Smoke Grey Slight gloss. Lighter, milkier grey.
- EZ 020 Mulberry Color fades.
- EZ 022 Flesh Tone Slightly textured sheen. Deeper, flesh color.
- EZ 023 Midnight Blue Dull, lighter blue.
- EZ 024 Royal Blue Green Slight sheen. Much deeper blue-green.
- EZ 025 Lemon Yellow Color dulls.
- EZ 026 Yellow Orange Dull but brighter yellow.
- EZ 027 Navajo Turquoise Slight sheen. Color yellows.
- EZ 028 Leaf Green Much darker olive green.
- EZ 030 Rose Color fades.
- EZ 031 Light Blue Much darker blue.



E-Z Stroke[™] Translucent Underglazes (continued)

- EZ 032 Peacock Green Slight sheen. Color yellows.
- EZ 033 Ivy Green Changes to a dull medium olive green.
- EZ 034 Orange Slight sheen. Much stronger color with a surface texture in heavier areas.
- EZ 035 Dutch Blue Dull, lighter milkier blue.
- EZ 037 Black Dull black.
- EZ 038 Medium Mahogany Slight sheen. Color changes to a shade of light brown.
- EZ 039 Dark Brown Nice satin, Lighter color. More of a chocolate brown.
- EZ 041 Denim Blue Color darkens to teal.
- EZ 042 Teal Slight sheen. Milkier, weaker blue-teal.
- EZ 043 Mint Julep Dull, milky blue-green.
- EZ 044 Cobblestone Satin sheen. Much darker brown.
- EZ 047 Thundercloud Grey Slight sheen. Color true.
- EZ 048 Mesa Clay Color fades.
- EZ 050 Pueblo Purple Color changes to a medium blue.
- EZ 052 Pecos Pink Color fades.
- EZ 053 Hacienda Jade Slight gloss. Color deeper and bluer.
- EZ 054 Papago Turquoise Slightly milkier and lighter color.
- EZ 055 Indian Summer Color changes to a dark brown.
- EZ 056 Brick Red Very little change in color.
- EZ 057 Coral Red Very little change in color.
- EZ 058 Poppy Orange Very little change in color.

- EZ 061 Petal Pink Very little change in color.
- EZ 063 Wine Berry Color deeper and bluer.
- EZ 064 Concord Grape Violet turned to a pale greenish blue.
- EZ 065 Periwinkle Medium blue.
- EZ 066 Morning Glory Deeper blue.
- EZ 067 True Taupe Faded to a green-brown.
- EZ 068 Roasted Chestnut Much lighter yellow-brown.
- EZ 069 Azure Blue Not recommended for cone 6 firing.
- EZ 070 Olive Green Darker shade of yellow/green.
- EZ 071 Dark Olive Not recommended for cone 6 firing.
- EZ 072 Romaine Slight sheen. Color darkens.
- EZ 073 Violet Slight gloss. Color change from pink to blue-grey.
- EZ 074 Dark Navy Slight sheen. Color darkens.
- EZ 075 Passion Red Color darkens.
- EZ 101 Neon Yellow Color darkens.
- EZ 102 Neon Blue Color darkens.
- EZ 103 Neon Chartreuse Slight sheen. Color darkens and shifts to green side.
- EZ 104 Neon Orange Slight sheen. Color darkens.
- EZ 105 Neon Green Semi-gloss. Color darkens to brown with streaks of neon green.
- EZ 106 Neon Red Slight sheen. Color darkens.

Courtyard™ Art Glazes

- CY 102 Sagebrush Very fluid. Crazing will occur. Color shift to grey/ green.
- CY 103 Desert Pine Very fluid. Color shift to brown.
- CY 104 Mediterranean Olive Very fluid. Crazing will occur. Darker color without the specks.
- CY 108 Cactus Sand Very fluid. Crazing will occur. Color shift to yellow. No specks are present.
- CY 110 Iron Ore Very fluid. Crazing will occur. Darker color without the specks. • CY 112 Saddle Clove - Very fluid. Crazing will occur. Color looks burnt
- without specks. • CY 113 Hearthstone – Very fluid. Crazing will occur. Color shift to
- yellow. No specks are present. • CY 116 Lava Slate – Very fluid. Crazing will occur. Color is translucent
- without specks.
- CY 117 Sand Very fluid. Crazing will occur. Color shift to yellow. No specks are present.

- CY 118 Pumpkin Spice Very fluid. Crazing will occur. Color shift to brown with red specks.
- CY 119 Golden Horizon Very fluid. Crazing will occur. Color shift to brown with red specks.
- CY 120 Harvest Plains Very fluid. Crazing will occur. Color shift to greenish brown.
- CY 121 Molasses Very fluid. Crazing will occur. Translucent. Color shift to greenish brown.
- CY 122 Rustic Sunset Very fluid. Crazing will occur. Translucent. Color shift to brown.
- CY 123 Rich Rust Very fluid. Crazing will occur. Translucent. Color shift to brown.
- CY 124 Fireluster Very fluid. Crazing will occur. Translucent. Color shift to greenish brown.

Designer Glazes™

- DG 201 Distressed Denim Not recommended for cone 6 firing.
- DG 202 Organza Orange Very fluid. Creates a darker color.
- DG 203 Carbon Chiffon Glossy with blue tones.
- DG 204 Natural Linen Very fluid. Crazing will occur. Creates a solid, darker color. All specks are lost.
- DG 205 Crimson Chenille Color is a burnt brown-red.
- DG 206 Forest Flannel Slightly fluid. Color loses blue/green tones and is on the brown side.
- DG 207 Saffron Silk Very fluid. Color is more brown than yellow.
- DG 208 Khaki Canvas Very fluid. Crazing will occur. Creates a solid, darker color. All specks are lost.

- DG 209 Teal Tweed Very fluid. Crazing will occur. Creates a solid, darker color. All specks are lost.
- DG 210 Cashmere Crème Color darkens.
- DG 211 Maize Twill Color darkens.
- DG 212 Celery Charmeuse Grey/green in color.
- DG 213 Seafoam Sateen Color darkens.
- DG 214 Sienna Suede Slightly fluid. Brown tones more pronounced than red.

Specialty Products™

- SY 546 Snow Not recommended for cone 6 firing.
- SY 1024 Antique Pewter Very little color change. Crazing may occur.
- SY 1025 Heirloom Silver Very little color change. Crazing will occur.